

Applicant : George Cintra et al.  
Serial No. : 10/034,901  
Filed : December 27, 2001  
Page : 2 of 11

Attorney's Docket No.: 08935-249001 / M-4965

Amendments to the Claims:

This listing of claims replaces all prior versions and listings of claims in the application:

Listing of Claims:

1. (Currently Amended) A method of making a battery electrode, the method comprising:  
forming a first layer comprising a cathode mixture on a substrate;  
removing the substrate from the first layer; and  
incorporating the first layer into the battery electrode,  
wherein the cathode mixture is in the form of a slurry.
2. (Canceled)
3. (Original) The method of claim 1, wherein the substrate comprises a material selected from a group consisting of a polymer, a metal, and paper.
4. (Original) The method of claim 1, wherein the substrate comprises a polymer.
5. (Withdrawn) The method of claim 1, further comprising:  
forming a second layer comprising the cathode mixture; and  
contacting the second layer with the first layer.
6. (Withdrawn) The method of claim 5, further comprising calendering the first and second layers.

Applicant : George Cintra et al.  
Serial No. : 10/034,901  
Filed : December 27, 2001  
Page : 3 of 11

Attorney's Docket No.: 08935-249001 / M-4965

7. (Withdrawn) The method of claim 5, further comprising calendaring the first and second layers under heat.

8. (Withdrawn) The method of claim 5, wherein contacting the second layer with the first layer increases the density of the first and second layers.

9. (Original) The method of claim 1, further comprising contacting the separated first layer with a current collector.

10. (Original) The method of claim 9, further comprising bonding the separated first layer and the current collector under pressure.

11. (Original) The method of claim 9, wherein the current collector includes an electrically conductive binder.

12. (Withdrawn) The method of claim 1, further comprising laminating the first layer to a plurality of layers, each one of the plurality of layers comprising a cathode material.

13. (Withdrawn) The method of claim 12, wherein the cathode material is a selected from a group consisting of a cathode active material, a binder, and a conductive aid.

14. (Previously Presented) The method of claim 1, wherein forming the first layer or removing the substrate is performed in a continuous process.

15. (Previously Presented) The method of claim 1, wherein forming the first layer and removing the substrate are performed in a continuous process.

16. (Withdrawn) A method of making a battery electrode, the method comprising:

Applicant : George Cintra et al.  
Serial No. : 10/034,901  
Filed : December 27, 2001  
Page : 4 of 11

Attorney's Docket No.: 08935-249001 / M-4965

- (a) forming a first layer comprising a first cathode mixture on a substrate;
- (b) removing the substrate from the first layer;
- (c) laminating the first layer to a second layer comprising a second cathode mixture; and
- (d) incorporating the laminated first and second layers into the battery electrode.

17. (Withdrawn) The method of claim 16, wherein the first and second cathode mixtures are substantially the same.

18. (Withdrawn) The method of claim 16, wherein the first and second cathode mixtures are different.

19. (Withdrawn) The method of claim 18, wherein the first and second mixtures have different chemical compositions.

20. (Withdrawn) The method of claim 16, wherein laminating includes calendering the first and second layers.

21. (Withdrawn) The method of claim 16, further comprising bonding the laminated first and second layers to a current collector.

22. (Withdrawn) A battery cathode having a thickness greater than about 100 micrometers.

23. (Withdrawn) A battery cathode having a current density greater than about 1mA/cm<sup>2</sup>.

24. (Withdrawn) A battery cathode formed of a plurality of layers, each layer comprising a cathode material.

Applicant : George Cintra et al.  
Serial No. : 10/034,901  
Filed : December 27, 2001  
Page : 5 of 11

Attorney's Docket No.: 08935-249001 / M-4965

25. (Withdrawn) The cathode of claim 24, wherein the cathode material is selected from a group consisting of a cathode active material, a binder, and a conductive aid.

26. (Withdrawn) The cathode of claim 24, wherein at least two of the layers have different porosities.

27. (Withdrawn) The cathode of claim 24, wherein at least two of the layers have different electronic conductivities.

28. (Withdrawn) The cathode of claim 24, wherein at least two of the layers have different chemical compositions.

29. (Withdrawn) The cathode of claim 24, wherein at least two of the layers have different concentrations of a binder.

30. (Withdrawn) The cathode of claim 24, further comprising a current collector in contact with one of the layers.

31. (Withdrawn) The cathode of claim 30, wherein the current collector comprises a conductive adhesive.

32. (Withdrawn) The cathode of claim 30, wherein the layers have increasing porosities relative to the distance from the current collector.

33. (Withdrawn) The cathode of claim 31, wherein the layers have increasing electronic conductivities relative to the distance from the current collector.

Applicant : George Cintra et al.  
Serial No. : 10/034,901  
Filed : December 27, 2001  
Page : 6 of 11

Attorney's Docket No.: 08935-249001 / M-4965

34. (Currently Amended) ~~The method of claim 1,~~ A method of making a battery electrode, the method comprising:

forming a first layer comprising a cathode mixture on a substrate;

removing the substrate from the first layer; and

incorporating the first layer into the battery electrode,

wherein the cathode mixture ~~comprising~~ comprises an electrode active material and a binder.

35. (Currently Amended) The method of claim ~~[[1]]~~ 34, wherein the binder comprises a polymer.

36. (Previously Presented) The method of claim 35, wherein the binder is selected from the group consisting of polyvinylidene fluoride, hexafluoropropylene, and polytetrafluoroethylene.

37. (Currently Amended) The method of claim ~~[[1]]~~ 34, wherein the cathode mixture further comprises a solvent.

38. (Previously Presented) The method of claim 37, wherein the solvent is selected from the group consisting of acetone, methyl ethyl ketone, diisobutyl ketone, methylpyrrolidone, and methyl isobutyl ketone.

39. (Previously Presented) The method of claim 37, further comprising removing a portion of the solvent after forming the first layer on the substrate.

40. (Currently Amended) The method of claim ~~[[1]]~~ 34, wherein the cathode mixture further comprises a conductive aid.

Applicant : George Cintra et al.  
Serial No. : 10/034,901  
Filed : December 27, 2001  
Page : 7 of 11

Attorney's Docket No.: 08935-249001 / M-4965

41. (Previously Presented) The method of claim 40, wherein the conductive aid comprises carbon.

42. (Previously Presented) A method of making a battery electrode, the method comprising:

forming a first layer comprising a cathode mixture on a substrate, the cathode mixture comprising an electrode active material and a solvent;  
removing the substrate from the first layer; and  
incorporating the first layer into the battery electrode.

43. (Previously Presented) The method of claim 42, wherein the solvent is selected from the group consisting of acetone, methyl ethyl ketone, diisobutyl ketone, methylpyrrolidone, and methyl isobutyl ketone.

44. (Currently Amended) A method of making a battery electrode, the method comprising:

forming a first layer comprising a cathode slurry mixture on a substrate;  
removing the substrate from the first layer; and  
incorporating the first layer into the battery electrode,  
wherein the cathode mixture comprises an electrode active material, a conductive aid, a binder, and a solvent.

45. (Canceled)